

P.V.C . Resin

Type	S-57	S-60	S-65	S-70
Appearance	W.P.*	W.P.	W.P.	W.P.
Inherent Viscosity	0.67-0.72	0.74-0.79	0.85-0.91	0.98-1.02
K-Value	56-58	59-61	64-66	69-71
Particle Size				
%Retained on 40 Mesh	Nil	Nil	Nil	Nil
%Retained on 200 Mesh	=> 85	=> 85	=> 85	=> 85
Porosity (ML/GR)	0.05-0.2	0.05-0.22	0.1-0.26	0.2-0.32
Volatile Matter (Heat Loss)%Max	0.7	0.7	0.7	0.7
Bulk Density(GR/CC) (Apparent)	0.5-0.62	0.55-0.61	0.46-0.60	0.44-0.5
Dark Resin (Per 10 SQ.IN.)	0-10	0-10	0-10	0-10

*White Powder,
25 Kg Bag,
750-1000 Kg Brg Bag*