

1) Product Description :
" 7000" F is a high density polyethylene

2) Application:

- Enhanced ultra thin film.

3) Typical Data

PROPERTY	TEST	UNIT	TYPICAL VALUE*
Density (23 °C)	ISO 1183	g/cm ³	0.952
Melt Flow Rate (190 °C/2.16kg)	ASTM D 1238	g/10min	0.04
Melt Flow Rate (190 °C/21.6 kg)	ASTM D 1238	g/10min	---
Stress at Yield Point	ASTM D 638	Kg/ cm ²	250
Stress at Break	ASTM D 638	Kg/ cm ²	390
Elongation at Break	ASTM D 638	%	Above 500
Izod Impact	ASTM D 256	kg.cm/cm	30
Stress Cracking Resistance	ASTM D 1693	hr	Above 600
Melting Point	ASTM D 2117	°C	131

*Typical Values;not to be construed as specifications.

Producer: Mehr Petrochemical Co.

Licensor: Mitsui

Packing: 25 kg Plastic Bag

Petrochemical Commercial Co.(PCC)
P.O. BOX: 19395/4619, TEHRAN-IRAN
E-mail: pcc@petrochem-ir.net
Web site:<http://petrochem-ir.net>

For more information please contact us at:
Telefax: +98 21 88788987-88889672-88788007-88799537
Telex: +98 21 216924-5